



# Personalized scaffolding technologies for alveolar bone regenerative medicine

Ning Yu<sup>1</sup>  | Trang Nguyen<sup>1</sup> | Young D. Cho<sup>1,2</sup> | Nolan M. Kavanagh<sup>1</sup> | Iya Ghassib<sup>1</sup> | William V. Giannobile<sup>1,3,4</sup> 

<sup>1</sup>Department of Periodontics and Oral Medicine, School of Dentistry, University of Michigan, Ann Arbor, Michigan

<sup>2</sup>Department of Periodontology, School of Dentistry and Dental Research Institute, Seoul National University, Seoul, Korea

<sup>3</sup>Department of Biomedical Engineering, College of Engineering, University of Michigan College of Engineering, Ann Arbor, Michigan

<sup>4</sup>Biointerfaces Institute, University of Michigan North Campus Research Complex, Ann Arbor, Michigan

## Correspondence

William V. Giannobile, Department of Periodontics and Oral Medicine, University of Michigan School of Dentistry, Ann Arbor, MI. Email: wgiannob@umich.edu

## Funding information

NIH/NIDCR, Grant/Award Number: DE U24 DE026915; The ITI Foundation; Osteology Foundation

## Structured Abstract

The reconstruction of alveolar bone defects associated with teeth and dental implants remains a clinical challenge in the treatment of patients affected by disease or injury of the alveolus. The aim of this review was to provide an overview on advances made in the use of personalized scaffolding technologies coupled with biologics, cells and gene therapies that offer future clinical applications for the treatment of patients requiring periodontal and alveolar bone regeneration. Over the past decade, advancements in three-dimensional (3D) imaging acquisition technologies such as cone-beam computed tomography (CBCT) and precise scaffold fabrication methods such as 3D bioprinting have resulted in personalized scaffolding constructs based on individual patient-specific anatomical data. Furthermore, 'fiber-guiding' scaffold designs utilize topographical cues to guide ligamentous fibers to form in orientation towards the root surface to improve tooth support. Therefore, a topic-focused literature search was conducted looking into fiber-guiding and image-based scaffolds and their associated clinical applications.

## KEYWORDS

3D printing, imaging, periodontal regeneration, scaffolds, tissue engineering


## 1 | INTRODUCTION

The key components of tissue engineering encompass proliferating cells, biocompatible scaffolds, biological signals and an appropriate blood supply. Regenerative medicine in the periodontal and alveolar bone fields follows the general principles of tissue engineering, while possessing several unique aspects. Regeneration around teeth supporting structures require a careful consideration of the future mechanical loading. The dynamic microbial challenges that the newly regenerated tissues constantly face make the pathogen control in periodontal regeneration a critical aspect (Figure 1A).<sup>1,2</sup>

In periodontal tissue engineering, both resident cells and distant stem cell-like progenitors have been intensely studied for both preclinical and clinical applications. Gingival tissue and periodontal ligament (PDL) harbour cells that possess the abilities to restore the

damaged periodontal and alveolar bone architectures.<sup>3</sup> Gingival fibroblasts have demonstrated potent bone formation properties; PDL cells enhance both bone and ligament repair.<sup>4,5</sup> Mesenchymal stem cells (MSCs) derived from various lineages also have strong properties for bone regenerative medicine.<sup>6</sup>

Designing and assembling biocompatible scaffolds to house the oral regenerative cells maximizes the outcomes of tissue engineering. An 'ideal' scaffold should contain a porous architecture to withstand a desired mechanical function, while at the same time to allow a mass transport for nutrients and growth factors contributing to the reparative process.<sup>7</sup> Advancements in three-dimensional (3D) imaging methods and 3D printing technologies make scaffold fabrications much more suitable for personalized reconstruction of complex topographies of periodontal osseous defects.<sup>8</sup>



**FIGURE 1** Principles and application of periodontal tissue bioengineering. A. Components of periodontal tissue engineering. Six factors constitute for successful periodontal tissue engineering: cells, signal, scaffold, mechanical loading, pathogen control and ideal blood supply. B. Examples of fiber guidance in periodontal tissue regeneration. On the upper left panel: Scanning electron microscopy (SEM) image of a micropatterned scaffold with grooves, a topographical cue to guide the aligned formation of new ligamentous tissue; on the upper middle panel: an illustration of PDL fiber-guiding scaffold (green) and amorphous bone scaffold (blue) against the tooth surface; on the upper right panel: SEM image of micropatterned scaffolds seeded with human PDL cells (blue arrows indicate the alignment of cells along the pillars of the scaffolds and their grooves). On the lower left panel: haematoxylin and eosin-stained (H&E) section of regenerated tissues in a rat that received a micropatterned scaffold with immobilized BMP-7 and PDGF-BB genes at a periodontal defect. The box and arrow indicate the regenerated ligamentous tissues and their oblique orientation, respectively. On the lower right panel: section of regenerated tissues in the same treatment group, stained for immunofluorescence (IF) with periostin (red), collagen III (green) and DAPI (blue). Periostin and collagen III are biomarkers for the formation of ligamentous tissue, and DAPI indicates cell nuclei. The collagen fibers are obliquely oriented and expressed throughout all the tissue due to the patterning. Adapted from Lin (2010) and Pilipchuk (2018)

How to incorporate the biological signals on top of the cells and scaffolds is another critically appraised topic in tissue engineering. Classically, gene transfer strategies adopt either a viral or non-viral approach. These carriers for biological factors can work directly on cells or indirectly on the scaffolds themselves. When applying directly on scaffold biomaterials, carriers can be covalently immobilized utilizing a reactive polymer coating prepared via chemical vapour deposition (CVD) polymerization of substituted paracyclophanes onto the scaffolds.<sup>9</sup> When working on cells, the conventional cell transduction/transfection methods have been widely adopted.

## 2 | PDL FIBER-GUIDING SCAFFOLDS

The topography of scaffolds serves as structural constraints for the tissue regeneration approaches. When being assigned to an optimized surface

topography, scaffolds can induce cell adhesion, migration, differentiation, as well as trigger certain molecular pathways, which can have longer lasting impacts on cellular function, beyond the period of regeneration.<sup>10</sup>

A critical component of the scaffolds' topography is the specific architecture design. The concept of fiber-guiding scaffold originated from the utilization of the pillars, which can induce a spontaneous alignment of PDLs. Park et al. designed mold-casted polymeric scaffolds with 'pillars' that ran perpendicularly against the tooth root in vivo.<sup>11</sup> The fiber-guiding design allowed the PDL cells and associated fibers to grow in an oriented fashion, mimicking how the Sharpey's fibers can connect the bundle bone to the cementum. The fiber-guiding scaffold also ensures a high customization, as a pre-surgical CT scan would acquire the defect's anatomical data for fabricating the scaffolds.<sup>11</sup> Building upon these efforts, Pilipchuk et al. included surface topographical cues on the fiber-guiding scaffolds to enhance cell attachment and growth. A micropatterned polycaprolactone

(PCL) film-containing pillars with microgrooves featuring specific depths and widths considerably increased the fraction of the aligned cells, surface treatments and enhanced cellular adhesions.<sup>12</sup> PCL is a hydrolytically degradable polymer that has been approved by the Food and Drug Administration. More recently, the micropatterned fiber-guiding scaffolds were tested in an alveolar fenestration animal model.<sup>13</sup> Additionally, the novel CVD surface treatment method was utilized to permit the immobilization of the adenoviral gene therapy vectors. The results have demonstrated strong potential of the combined strategies of fiber-guiding scaffolds and gene therapy in restoring the lost periodontium (Figure 1B).

In addition to the pillar and groove designs that constitute the core components of fiber-guiding scaffolds, lessons learned from neuron regeneration have shed light on many intraluminal scaffold designs that may benefit periodontal tissue regeneration. Ahn et al. tethered carbon nanotubes (CNTs) onto glass conduits to guide the regeneration of transected sciatic nerves *in vivo*.<sup>14</sup> As a result of the nanoarchitecture, neurites grew longer and led to more directional outgrowth *in vitro*.<sup>14</sup> CNTs were well suited for neuronal regeneration, as they themselves are electrically conductive, which may favourably influence the regenerative mechanisms. CNTs have been studied in bone regeneration. Li et al. reported that CNTs promoted the osteogenic differentiation of the adipose-derived MSCs by inducing multiple bone forming proteins.<sup>15</sup> Currently, there have been no reports on the utilization of CNTs in PDL regeneration. However, the electrically conductive nature with the addition of tubules mechanical property could be promising in ligamentous tissue regeneration.

Therefore, periodontal tissue engineering strategies should consider the fiber guidance design. Architectures can be chosen to guide tissues in a desired orientation, whether directional as for PDL or non-directional as for bone. Topographical cues should dial up (or down) the appropriate cellular processes, such as enhancing mineralization to encourage osteogenesis. Non-physical cues, such as magnetism or conductivity, can be paired to tissue types (such as bone or nerves) for which they desirably intervene on regenerative mechanisms.

## 2.1 | Image-based scaffolds to adapt to periodontal and oral topography

As technology is advancing, 3D bioprinting enables fabrication of a customized biomedical tool with a precise shape and function based on individual-specific anatomical data.<sup>16</sup> In image-based personalized tissue engineering, 3D printing is used for making a scaffold via multi-step processes: (a) image acquisition; (b) image processing with DICOM conversion and STL file generation; (c) image post-processing: 3D reconstruction and 3D CAD modelling; and (d) rapid prototyping (RP): 3D printing and custom model fabrication (Figure 2).

### 2.1.1 | 3D Image acquisition

Precise data acquisition for the accurate production of personalized scaffolds is done using CBCT or magnetic resonance imaging image datasets. Scaffolds are produced based on computer-aided design/


computer-aided manufacturing (CAD/CAM). This entails generating the scaffold, on macro-, micro- and nanoscopic levels of architectural design which matches its proper function.<sup>17</sup> Patients' image data help to create the exterior shape of the scaffold and optimize the internal porous structure providing a balance between load bearing and biological factors. On the one hand, a microporous structure is needed to ensure adequate drug delivery, or if not, the structure may compromise the function of mechanical load bearing. These characteristics should be considered quantitatively, resulting in the final mechanical properties at least partially resembling those of the native tissues, if not entirely.<sup>7,18</sup>

### 2.1.2 | Image processing for scaffold fabrication

Technology is advancing to provide more attention to simulating the intricate internal and external tissue structures. There is a demand to develop imaging techniques that facilitate better understanding of structure and function, as well as enhance reproducibility of the scaffold. DICOM CT images are segmented and utilized in image-based CAD to create porous anatomical structures. Image-based computer designs and models are suited to produce anatomical implants and scaffolds.<sup>19</sup> Hollister et al. developed an image-based hierarchical design method, where the scaffold was designed with a local image voxel database and assigned with varying voxel densities. The porous scaffold design could follow either periodic or random geometric pore structures. In a separate voxel image dataset, the anatomical defect was assigned with voxel densities as well. Finally, the scaffold database can be integrated with image database of the anatomical defect to create the final tissue engineering scaffold design.<sup>19</sup> This scaffold designing approach allows an increased flexibility in design, therefore facilitates the use of a wide range of materials of different properties. The challenge of the scaffold design, on the other hand, necessitates the emergence of topology optimization, which is essentially an algorithm facilitating desirable scaffold properties.<sup>17</sup> In addition, to better visualize and mimic the anatomical structure, post-processing of the images is usually performed. The most common tools used are volume rendering and multi-planar reconstructions. Combining different segmentation algorithms provide greater accuracy in determining the region of interest for detailed and comprehensive analysis.<sup>20</sup> After post-processing, 3D reconstruction and CAD modelling strive to demonstrate conceptual behaviour of tissues, incorporating treatment outcomes.<sup>21</sup> It blends in the complex macro- and micro-structure of bone into one unique conformity. Additionally, it accommodates with principal stress on tissues, simulating different dynamic states of tissues. This shows a clear advancement in treatment planning in interdisciplinary dental fields.<sup>22</sup>

### 2.1.3 | Scaffold fabrication

The solid freeform fabrication (SFF) method enables production of individual-specific 3D scaffolds.<sup>16</sup> The SFF method makes a 3D scaffold controlling the materials or parameters based on CAD/CAM. This technique permits the following applications in tissue engineering: fused deposition modelling, stereolithography, selective laser



**FIGURE 2** Image-based scaffold design for alveolar bone bioengineering. Step 1: Image acquisition with a CBCT scan for hard tissue and intraoral scan for soft tissue; step 2: image pre-processing; the images from step 1 are integrated as a DICOM file, then converted to a STL file for preparing 3D printable condition; step 3: image post-processing; 3D volume visualization for optimization of scaffold shape; step 4: rapid prototyping; based on image processing, scaffolds are manufactured by the 3D printer. Step 5: clinical application; custom-fit scaffold is applied at the time of the reconstructive surgery

sintering and 3D bioprinting.<sup>23</sup> Meticulous planning is improved by RP techniques, whereby models could be simulated rapidly prior to actual fabrication of materials or implementation of regenerative methods. SFF and RP necessitate improvement in imaging and printing techniques. With this technology, prototyping is done prior to material manufacturing. It is also referred to as layer-by-layer fabrication. 3D treatment planning is quite useful in cases of periodontal regeneration. Van Dyke et al. demonstrated that nano-proresolving medicines designed for treatment of inflammation-induced bone loss showed strong potential *in vivo*.<sup>24</sup> SEM images facilitate the quantification of collagen fibers as well as marking of their orientation. The complexity in regeneration is marked by the various types of tissues as well as their adaptability to their function, simulating the entire native architecture of newly repaired tissues.

### 2.1.4 | Clinical applications of personalized scaffolding technology for periodontal and alveolar bone engineering

Given the complexity of osseous structures requiring new blood formation, new technologies are employing microvascular techniques to

enhance the reconstruction of large defects. For example, 2D microcapillaries are stacked, forming blood circulation to ensure optimum regeneration. Tissue fabrication is further investigated by deposition of materials with live cells, that is, via bioprinting. With the advent of CT and sequential sectioning, a clear process line is developed, marked by pre-processing for the first stage of tissue or organ printing.<sup>25</sup> Organ printing uses the principle of cellular self-assembly into tissues, as dictated by developmental biology.<sup>26</sup> There are various clinical applications of personalized scaffolding technology in periodontal tissue and alveolar bone engineering as described below.

### 2.1.5 | Periodontal tissue regeneration

3D-printed scaffolding technology has been developed in the attempt to regenerate the periodontal tissues surrounding natural teeth. Scaffolds that are designed by computer-based technologies precisely fill the region-specific defect space, creating an optimal environment for cellular growth and angiogenesis. Rasperini et al. reported the first clinical application of personalized scaffolding in periodontal tissue regeneration.<sup>27</sup> A customized scaffold was 3D-printed to adapt to an osseous defect of a cuspid, using a

prototype model according to the CBCT scan. The scaffolding materials used were slowly degrading PCL/4% hydroxyapatite (HA). Prior to delivery to the patient's defect, the scaffold was immersed in platelet-derived growth factor BB as an FDA-approved biological. At 14 months, a biopsy of the scaffold construct was evaluated and it was noted that while the scaffold resorbed (~25% by this time), there was evidence on new connective tissue and bone formation in the construct. This case suggests that more slowly resorbing biomaterials may not be appropriate for periodontal repair. Many additional periodontal applications have included a combination on PCL and PLGA (poly-lactic-co-glycolic acid) blends that will drive a more rapid rate of matrix resorption *in vivo*.<sup>11,13,28,29</sup> Currently, models are being improved using personalized scaffolding approaches to treat challenging furcation defects where wound stability and space maintenance are crucial (Figure 3). A 3D-printed scaffold made from an equitable ratio of PCL and PLGA has also exhibited an ability to carry therapeutic genes that benefits bone regeneration. This novel cell-based gene delivery with personalized scaffolding has showed promising effects on periodontal engineering.

### 2.1.6 | Craniofacial reconstruction


Personalized scaffolding technology utilizing 3D-imaging and 3D-printing has contributed greatly new prototype biomaterials for craniofacial reconstruction. Conventionally, dental and skeletal relationships are analysed through wax-ups, 2D radiographs, photographs and articulators that are time-consuming and cumbersome. In many complex cases, such as facial asymmetry, skeletal movements in relation with the complex are difficult to be established and analysed using traditional 2D approaches.<sup>30</sup> In these cases, 3D

imaging builds a platform on which dental and skeletal features are documented accurately to permit a precise diagnostic system and hence benefits the efficiency of treatment planning.<sup>31</sup>

During diagnostic work-up, 3D imaging enables an integration of dental, skeletal and soft tissue relationships through their movements at the cranial base, providing relevant anatomical features. Furthermore, using 3D printing, skeletal components can be simulated and translated into physical models through the customized fabrication of appliances, which could serve as a surgical splint and/or a stainless-steel arch wire. During the treatment planning phase, orthodontists and oral surgeons can utilize these appliances to review the relevant anatomical movements and discuss the detailed surgical procedures and anticipated surgical end point.<sup>22</sup> This approach helps to reduce the surgical time and fulfil the aesthetic demands.

### 2.1.7 | Alveolar bone regeneration

Personalized scaffolding technology has been increasingly used in the alveolar ridge reconstruction for the implant site development. 3D-printed diagnostic models and preoperative templates are widely applied for ridge augmentation in severe vertical and horizontal bony defects.<sup>32,33</sup> Despite the advanced applications of CBCT combined with CAD/CAM fabrications, current 3D printing for alveolar ridge augmentation is limited using printing templates, which might not directly induce bone regeneration as inert biomaterials. Considering its clinical potential in other specialties, future directions suggest applying 3D technology using osseoinductive and osteoconductive biomaterials will better enhance bone and tissue regeneration for vertical and horizontal ridge augmentation supporting implant placement.



**FIGURE 3** Personalized scaffold technologies for periodontal engineering in furcation defects. Personalized scaffolding process consists of three stages: The scaffold can be initially designed based on the tooth and bone morphology taken from a CBCT scanning before treatment. The scaffold construct then is fabricated from a balanced ratio of polymeric biomaterials such as PCL and/or PLGA using 3D printing technology. The scaffolds can be coated with genes for osteogenic factors using chemical vapor deposition (CVD) technology to allow gene vector release after cell attachment to the tissue scaffolds



In the rehabilitation of partially or fully edentulous patients with a lack of maxillary posterior bone support, sinus floor augmentation is required prior to dental implant placement. An anatomically sinus-specific block graft can be fabricated via 3D technology for bone augmentation has recently been introduced in a clinical trial for lateral sinus augmentation.<sup>34</sup> Briefly, the scaffold manufacturing process applies a virtual planning and designing a custom-made scaffold and then a 3D fabrication of the scaffold is performed using the CAM technique. The customized block graft is created from an original HA block using a cutting guide also made from 3D image-based analysis and planning.

In summary, utilizing 3D imaging and 3D-printing for fabrication of customized scaffolding technology to regenerate periodontal tissue and alveolar bone is a rapidly growing research field. With continued advancement of novel 3D imaging technologies, broader and more accurate clinical applications are anticipated combining printing with imaging to customized reconstructive scaffolds to repair large bone defects in the jaws.

### 3 | FUTURE DIRECTIONS

The implementation of personalized or customized regenerative scaffold technologies for periodontal and alveolar ridge regeneration is coming very close to reality in clinical practice. The more routine use of 3D, high-resolution imaging of both soft and hard tissues makes integration with system software more feasible for reconstruction at the bone-tooth, bone-implant interface as well as for larger osseous defects of the alveolar ridge and craniofacial complex. Advances in bioprinting now allow the delivery of cells, extracellular matrices, genes and/or biological agents onto polymeric, ceramic and natural biomaterials. These technological developments in regenerative medicine create exciting solutions for surgeons and restorative dentists for predictable regenerative therapies to improve patient care.<sup>35</sup>

### ACKNOWLEDGEMENTS

Special acknowledgement for illustrations and graphic design contributions is given to Kenneth Rieger at the University of Michigan School of Dentistry graphic design department. This work was supported in part by NIH/NIDCR DE U24 DE026915 to W.V.G., The ITI Foundation to T.N. and the Osteology Foundation to Y.D.C.

### CONFLICT OF INTEREST

The authors claim no conflict of interest related to the publication of this article.

### ORCID

Ning Yu  <https://orcid.org/0000-0002-3046-4338>

William V. Giannobile  <https://orcid.org/0000-0002-7102-9746>

### REFERENCES

- Lin Z. *The function and regulation of LIM domain mineralization protein (LMP) in periodontal ligament progenitor cells*. PhD, University of Michigan, Ann Arbor, MI; 2010.
- Larsson L, Decker AM, Nibali L, Pilipchuk SP, Berglundh T, Giannobile WV. Regenerative medicine for periodontal and peri-implant diseases. *J Dent Res*. 2016;95(3):255-266.
- Seo BM, Miura M, Gronthos S, Bartold PM, Batouli S, Brahim J, et al. Investigation of multipotent postnatal stem cells from human periodontal ligament. *Lancet*. 2004;364(9429):149-155.
- Yu N, Oortgiesen DA, Bronckers AL, Yang F, Walboomers XF, Jansen JA. Enhanced periodontal tissue regeneration by periodontal cell implantation. *J Clin Periodontol*. 2013;40(7):698-706.
- Feng F, Akiyama K, Liu Y, Yamaza T, Wang TM, Chen JH, et al. Utility of PDL progenitors for in vivo tissue regeneration: a report of 3 cases. *Oral Dis*. 2010;16(1):20-28.
- Kaigler D, Pagni G, Park CH, Braun TM, Holman LA, Yi E, et al. Stem cell therapy for craniofacial bone regeneration: a randomized, controlled feasibility trial. *Cell Transplant*. 2013;22(5):767-777.
- Hollister SJ, Lin CY, Saito E, Lin CY, Schek RD, Taboas JM, et al. Engineering craniofacial scaffolds. *Orthod Craniofac Res*. 2005;8(3):162-173.
- Obregon F, Vaquette C, Ivanovski S, Huttmacher DW, Bertassoni LE. Three-dimensional bioprinting for regenerative dentistry and craniofacial tissue engineering. *J Dent Res*. 2015;94(9 Suppl.):143S-152S.
- Hao J, Cheng KC, Kruger LG, Larsson L, Sugai JV, Lahann J, et al. Multigrowth factor delivery via immobilization of gene therapy vectors. *Adv Mater*. 2016;28(16):3145-3151.
- Larsson L, Pilipchuk SP, Giannobile WV, Castilho RM. When epigenetics meets bioengineering – a material characteristics and surface topography perspective. *J Biomed Mater Res B Appl Biomater*. 2018;106(5):2065-2071.
- Park CH, Rios HF, Taut AD, Padiol-Molina M, Flanagan CL, Pilipchuk SP, et al. Image-based, fiber guiding scaffolds: a platform for regenerating tissue interfaces. *Tissue Eng Part C Methods*. 2014;20(7):533-542.
- Pilipchuk SP, Monje A, Jiao Y, Hao J, Kruger L, Flanagan CL, et al. Integration of 3D printed and micropatterned polycaprolactone scaffolds for guidance of oriented collagenous tissue formation in vivo. *Adv Healthc Mater*. 2016;5(6):676-687.
- Pilipchuk SP, Fretwurst T, Yu N, et al. Micropatterned scaffolds with immobilized growth factor genes regenerate bone and periodontal ligament-like tissues. *Adv Healthc Mater*. 2018;7:e1800750.
- Ahn HS, Hwang JY, Kim MS, Lee JY, Kim JW, Kim HS, et al. Carbon-nanotube-interfaced glass fiber scaffold for regeneration of transected sciatic nerve. *Acta Biomater*. 2015;13:324-334.
- Li X, Liu H, Niu X, Yu B, Fan Y, Feng Q, et al. The use of carbon nanotubes to induce osteogenic differentiation of human adipose-derived MSCs in vitro and ectopic bone formation in vivo. *Biomaterials*. 2012;33(19):4818-4827.
- Chia HN, Wu BM. Recent advances in 3D printing of biomaterials. *J Biol Eng*. 2015;9:4.
- Hollister SJ. Porous scaffold design for tissue engineering. *Nat Mater*. 2005;4(7):518-524.
- Park SH, Kang BK, Lee JE, Chun SW, Jang K, Kim YH, et al. Design and fabrication of a thin-walled free-form scaffold on the basis of medical image data and a 3d printed template: its potential use in bile duct regeneration. *ACS Appl Mater Interfaces*. 2017;9(14):12290-12298.
- Zopf DA, Mitsak AG, Flanagan CL, Wheeler M, Green GE, Hollister SJ. Computer aided-designed, 3-dimensionally printed porous tissue bioscaffolds for craniofacial soft tissue reconstruction. *Otolaryngol Head Neck Surg*. 2015;152(1):57-62.



20. Hutmacher DW. Scaffold design and fabrication technologies for engineering tissues—state of the art and future perspectives. *J Biomater Sci Polym Ed.* 2001;12(1):107-124.
21. Hollister SJ, Kikuchi N. Homogenization theory and digital imaging: a basis for studying the mechanics and design principles of bone tissue. *Biotechnol Bioeng.* 1994;43(7):586-596.
22. Jheon AH, Oberoi S, Solem RC, Kapila S. Moving towards precision orthodontics: an evolving paradigm shift in the planning and delivery of customized orthodontic therapy. *Orthod Craniofac Res.* 2017;20(Suppl. 1):106-113.
23. Lee JW, Kim JY, Cho DW. Solid free-form fabrication technology and its application to bone tissue engineering. *Int J Stem Cells.* 2010;3(2):85-95.
24. Van Dyke TE, Hasturk H, Kantarci A, Freire MO, Nguyen D, Dalli J, et al. Proresolving nanomedicines activate bone regeneration in periodontitis. *J Dent Res.* 2015;94(1):148-156.
25. Mironov V, Boland T, Trusk T, Forgacs G, Markwald RR. Organ printing: computer-aided jet-based 3D tissue engineering. *Trends Biotechnol.* 2003;21(4):157-161.
26. Karch R, Neumann F, Neumann M, Schreiner W. A three-dimensional model for arterial tree representation, generated by constrained constructive optimization. *Comput Biol Med.* 1999;29(1):19-38.
27. Rasperini G, Pilipchuk SP, Flanagan CL, Park CH, Pagni G, Hollister SJ, et al. 3D-printed bioresorbable scaffold for periodontal repair. *J Dent Res.* 2015;94(9 Suppl.):153s-157s.
28. Wei G, Ma PX. Partially nanofibrous architecture of 3D tissue engineering scaffolds. *Biomaterials.* 2009;30(32):6426-6434.
29. Bottino MC, Pankajakshan D, Nor JE. Advanced scaffolds for dental pulp and periodontal regeneration. *Dent Clin N Am.* 2017;61(4):689-711.
30. Janakiraman N, Feinberg M, Vishwanath M, Nalaka Jayaratne YS, Steinbacher DM, Nanda R, et al. Integration of 3-dimensional surgical and orthodontic technologies with orthognathic “surgery-first” approach in the management of unilateral condylar hyperplasia. *Am J Orthod Dentofac Orthop.* 2015;148(6):1054-1066.
31. Edwards SP. Computer-assisted craniomaxillofacial surgery. *Oral Maxillofac Surg Clin North Am.* 2010;22(1):117-134.
32. Draenert FG, Gebhart F, Mitov G, Neff A. Biomaterial shell bending with 3D-printed templates in vertical and alveolar ridge augmentation: a technical note. *Oral Surg Oral Med Oral Pathol Oral Radiol.* 2017;123(6):651-660.
33. Al-Ardah A, Alqahtani N, AlHelal A, Goodacre B, Swamidass R, Garbacea A, et al. Using virtual ridge augmentation and 3D printing to fabricate a titanium mesh positioning device: a novel technique letter. *J Oral Implantol.* 2018;44:293-299.
34. Mangano F, Zecca P, Pozzi-Taubert S, Macchi A, Ricci M, Luongo G, et al. Maxillary sinus augmentation using computer-aided design/computer-aided manufacturing (CAD/CAM) technology. *Int J Med Robot.* 2013;9(3):331-338.
35. Giannobile WV, Chai Y, Chen Y, Healy KE, Klein O, Lane N, et al. Dental, oral, and craniofacial regenerative medicine: transforming biotechnologies for innovating patient care. *J Dent Res.* 2018;97(4):361-363.

**How to cite this article:** Yu N, Nguyen T, Cho YD, et al. Personalized scaffolding technologies for alveolar bone regenerative medicine. *Orthod Craniofac Res.* 2019;22(Suppl. 1):69-75. <https://doi.org/10.1111/ocr.12275>