

Air-Tolerant Poly(3-hexylthiophene) Synthesis via Catalyst-Transfer Polymerization

Tomohiro Kubo, Morgan S. Young, Kendra D. Souther, Matthew D. Hannigan, and Anne J. McNeil*

Department of Chemistry and Macromolecular Science and Engineering Program, University of Michigan, 930 North University Avenue, Ann Arbor, Michigan 48109-1055, United States

Correspondence to: Anne J. McNeil (E-mail: ajmcneil@umich.edu)

((Additional Supporting Information may be found in the online version of this article.))

ABSTRACT: The discovery of catalyst-transfer polymerization and its further developments have led to unprecedented control over the length and sequence of conjugated polymers. However, the methods themselves are technically challenging to perform due to the air- and moisture-sensitivities of the monomers and catalysts. Herein, we report a catalyst-transfer polymerization method that affords poly(3-hexylthiophene) in high yields without using an inert atmosphere. The synthesis capitalizes on a rapid Negishi cross-coupling using a moisture-tolerant organozinc monomer mediated by an air-stable Pd precatalyst. This simple method should make conjugated polymer synthesis more accessible to a broader range of researchers and may be generalizable to other monomer scaffolds.

KEYWORDS: catalyst-transfer polymerization, chain-growth polymerization, catalysis, conjugated polymers, palladium

INTRODUCTION

Organic conjugated polymers (CPs) have remained fascinating materials for chemists since the Nobel-prize winning observation of their conductivity in 1977.¹ Over the next 40 years, CPs were evaluated as the active materials in transistors,² light-emitting diodes,³ and solar cells.⁴ Although research in these traditional areas continues today, new CP-based applications have emerged. For example, in a recent perspective Swager suggested that the future of CPs is in superconductors, magneto-optic materials, and artificial muscles.⁵ Around the same time, Seferos and co-workers suggested the future of CPs is in electrical energy storage.⁶ Within these evolving contexts, Swager notes that “precision in [CP] synthesis is critical” to enabling these applications.⁵

Most conjugated polymers are still synthesized via step-growth polymerizations involving metal-catalyzed C–C bond forming reactions.⁷ This

synthetic approach is extremely versatile with respect to monomer structures, but often leads to polymers with broad dispersity and little control over the length, copolymer sequence, or end-groups. An alternative approach, known as catalyst-transfer polymerization (CTP), proceeds via a living, chain-growth mechanism.^{8,9,10,11,12,13,14,15,16,17} As a consequence, specific lengths, copolymer sequences, and end-groups can be targeted, and the resulting polymer’s dispersity (\bar{D}) is often narrow (< 2). Having such exquisite control over polymer architecture has led to numerous advances in the field, including higher performing materials.¹⁵ However, this method works best with only a subset of useful monomers (primarily small, electron-rich aromatic structures). In addition, the synthesis often requires an inert atmosphere due to moisture- and/or air-sensitive catalysts and reagents. As a result, researchers without access to specialized equipment must rely on collaborators or commercial suppliers to make

This is the author manuscript accepted for publication and has undergone full peer review but has not been through the copyediting, typesetting, pagination and proofreading process, which may lead to differences between this version and the Version of Record. Please cite this article as doi: [10.1002/pol.29912](https://doi.org/10.1002/pol.29912)

materials, limiting widespread exploration of CPs in electronic applications.

Recognizing this challenge, several recent papers have described a more 'user-friendly' conjugated polymer synthesis, in which the polymerization is performed in air.^{18,19} For example, Kanbara and co-workers reported an oxygen- and moisture-tolerant synthesis of thienopyrroledione-based conjugated polymers through a step-growth direct arylation polycondensation, wherein refluxing conditions effectively deoxygenated the solution.^{18,20} Most recently, Schoenebeck and coworkers demonstrated CP synthesis in air utilizing the high reactivity of a Pd(I) dimer-based catalyst, which enabled high conversions to be reached before appreciable monomer deactivation via quenching.¹⁹ One limitation of both studies is that control over the molar masses was not achieved, indicating non-living processes. Alternatively, Higashihara and co-workers reported a method for synthesizing regioregular poly(3-hexylthiophene) that was tolerant to protic impurities (e.g., MeOH) in the solvent using $t\text{Bu}_4\text{ZnLi}_2$ and Ni precatalysts. However, the polymerizations still required an inert argon atmosphere presumably due to ligand/catalyst deactivation.²¹

Herein, we describe an air-tolerant, living, chain-growth synthesis of poly(3-hexylthiophene) (P3HT) with bench-stable Pd precatalysts and organozinc reagents.^{22,23,24} All reactions were performed in a hood, with commercial reagents used as received, and without using an inert atmosphere. The process begins by generating an organozinc monomer in situ from a Grignard reagent and zinc pivalate.^{25,26,27} The magnesium pivalate by-product is believed to sequester trace water, serving as a desiccant. Next, the Negishi-based polymerization is mediated by an air-stable Pd precatalyst. This approach was inspired by Knochel and coworkers, who have reported similar open-to-air Negishi cross-couplings of aromatic small molecules.^{28,29,30} The resulting polymers were obtained with narrow dispersity, specified length, and with end-groups

consistent with a catalyst-transfer polymerization mechanism.

EXPERIMENTAL

All reagents and solvents were used as received and without further purification. All reactions were performed using 8 mL glass vials capped with a rubber septum. The reaction vials and stir bars were dried in an oven overnight and cooled to rt inside a desiccator filled with Drierite granules. Reagents were transferred using disposable plastic syringes and metal needles.

Monomer Synthesis (3HT_{Zn}). 2,5-Dibromo-3-hexylthiophene (0.050 mL, 0.23 mmol) and docosane (internal standard) were added to a vial which was capped with a septum. Then, anhydrous THF (1.2 mL) and *i*-PrMgCl (2.0 M in THF, 0.082 mL, 0.16 mmol) were sequentially added. The homogeneous solution was stirred for 10 min at rt. Then, a portion of this Grignard solution (1.0 mL, 0.13 mmol) was added to a separate vial containing Zn(OPiv)₂ (36 mg, 0.14 mmol). This solution was stirred for 10 min at rt.

Precatalyst Solution. In a separate vial, Pd-PEPPSI-IPent (2.9 mg, 0.0036 mmol) was dissolved in THF (0.8 mL).

Polymer Synthesis (P3HT). A portion of the precatalyst solution (0.5 mL, 0.0045 M in THF) was added to the organozinc solution. The reaction was stirred for 10 min at rt. Within the first min, the solution turned dark orange. The polymerization was quenched by adding aq. HCl (1.0 mL, 12 M) and extracted with DCM (2.0 mL). The organic layer was dried (MgSO₄) and filtered. A portion of this solution was concentrated and then re-dissolved in approx. 1 mL of THF, then analyzed by size-exclusion chromatography (SEC) to determine M_n and \mathcal{D} and by matrix-assisted laser-desorption time-of-flight mass spectrometry (MALDI-TOF-MS) to determine the end-groups. Another portion was analyzed by gas chromatography (GC) with a flame ionization detector (FID) to determine monomer conversion relative to an internal standard (docosane).

RESULTS AND DISCUSSION

Our synthetic approach is highlighted in Scheme 1. First, 2,5-dibromo-3-hexylthiophene is reacted with *i*-PrMgCl to generate a Grignard reagent (**3HT_{Mg}**) as a 79:21 mixture of regioisomers, as evidenced by GC analysis (Table S1). After 10 min, an aliquot of the **3HT_{Mg}** is added Zn(OPiv)₂ to generate the zinc-based monomer (**3HT_{Zn}**), with no change in the regioselectivity observed (Table S2). This process generates Mg(OPiv)₂ as a byproduct, which has been suggested by others to efficiently sequester adventitious water.²⁵ Next, the precatalyst (Pd-PEPPSI-IPent) is added to the **3HT_{Zn}** solution to generate **P3HT**. After 10 min, the polymerization is quenched and the polymer is extracted for analysis. **All of the above reactions were performed with solvents used as received and without an inert atmosphere. The reactions were performed in small vials capped with a septum, and the septum is temporarily removed when reagents are added.**

¹H NMR spectroscopic analysis reveals that the synthesized **P3HT** exhibits 63% regioregularity, indicating that both regioisomers of the **3HT_{Zn}** are consumed. **Indeed, our GC data reveals high conversions of both regioisomers, with the minor regioisomer having a slightly higher conversion (minor (93%) versus major (87%)), consistent with the low regioregularity. Presumably, switching to the I/Br monomer precursor (i.e., 2-bromo-3-hexyl-5-iodothiophene) would lead to P3HT with higher regioregularity, though the reaction temperature may need to be lowered to prevent undesired side-reactions (e.g., HI elimination from the in situ-generated 2-iodopropane.)** Analysis by SEC reveals that the number-average molar mass (*M_n*) is similar to the theoretical *M_n*, which is calculated based on the initial monomer/catalyst ratio and the monomer conversion (Table 1, entry 1).^{31,32} Additionally, the resulting polymer sample exhibits moderate dispersity (*Đ* ≈ 1.5). Combined, these results are consistent with a chain-growth mechanism.

SCHEME 1. Air-tolerant synthesis of poly(3-hexylthiophene) via catalyst-transfer polymerization.




Table 1. Polymerization data with varying reaction conditions.^{a,b}

entry	precatalyst	conditions	<i>M_n</i> (kg/mol)	<i>Đ</i>
1	IPent	in air	10.6	1.47
2	IPent	under N ₂	11.2	1.46
3	IPr	under N ₂	10.0	1.87
4	SIPr	under N ₂	17.8	1.81
5	IPent	ZnCl ₂	6.5	1.46
6	IPent	without Zn	3.9	1.47

^aEntries 5–6 were also performed under N₂. ^b*M_n* (theoretical) = 10 kg/mol for 100% monomer conversion.

To optimize this method, several commercially available, air-stable Pd-PEPPSI precatalysts (where PEPPSI stands for pyridine-enhanced precatalyst preparation, stabilization, and initiation) were screened **under an N₂ atmosphere** with the primary selection criterion being their ability to generate polymers with exclusively H/Br end groups, as measured using MALDI-TOF-MS. **These end-groups are indicative of a living, chain-growth mechanism³³ wherein the precatalyst initiates via two sequential transmetalation reactions and then continues to propagate without termination until quenching**

with acid. For comparison, the original IPent precatalyst yielded **P3HT** with exclusively H/Br chain ends, as evident in Figure 1. In contrast, both IPr and SIPr precatalysts afforded polymers with multiple chain-end identities, including Br/Br and H/H, as well as the desired H/Br (see SI Figures S2 and S4). These results are consistent with both catalyst disassociation (Br/Br) and the released Pd(0) catalyst undergoing subsequent initiation with monomer (H/H). In addition, although the IPr precatalyst gave polymer with the expected M_n , the dispersities were broader than with IPent (Table 1, entry 3). In contrast, the SIPr precatalyst gave both a much higher than expected M_n and a broader dispersity (Table 1, entry 4.) Although the mechanistic rationale for the improved results with the sterically demanding but conformationally flexible environment provided by IPent is unclear at this time, we note that Organ and co-workers previously observed that IPent was optimal for sterically congested substituted substrates.³⁴ For comparison, Ni(dppp)Cl₂ gave only oligomers with multiple end-group identities. Having identified IPent as a suitable precatalyst, we further probed the impact of the reaction conditions on the polymerization.




FIGURE 1. MALDI-TOF mass spectrum of **P3HT** prepared by Pd-PEPSSI-IPent precatalyst.

Control experiments revealed the importance of using Zn(OPiv)₂; for example, using a different zinc reagent (i.e., ZnCl₂) or using no zinc reagent resulted in polymers with a significantly lower

M_n (Table 1, entries 5 and 6), suggesting a slower polymerization. One hypothesis was that the slower rate might be due to prematurely quenched monomer, which would lower its effective concentration in solution and decrease the polymerization rate. Alternatively, the slower polymerization rate may simply be due to the different nucleophilicities of the organometallic species (**3HT**_{Mg} versus **3HT**_{Zn}), either due to the identity of the counterion or their aggregation state. To identify which factor was more important, we monitored the polymerization by periodically quenching aliquots with iodine. This method enabled us to distinguish prematurely quenched monomer (**3HT**_H) from unreacted monomer (**3HT**_I). The results, highlighted in Figure 2, showed rapid polymerization when Zn(OPiv)₂ was added (>90% conversion within 5 min). During this time, only ca. 10% of monomer was prematurely quenched. Without Zn(OPiv)₂, the polymerization was much slower (~20% conversion within 5 min) and a similar amount of the monomer was prematurely quenched (10%). Combined, these results suggest that the slower polymerization is not due to monomer quenching with adventitious moisture but instead that the Zn(OPiv)₂-based monomer is more nucleophilic, leading to a faster polymerization. The different reactivities of the Zn and Mg monomers may be useful for generating random, gradient, and block copolymers in situ.³⁵ Our earlier results (Table 1) also indicate that the form of ZnX₂ (where X = OPiv or Cl) plays an important, yet still not well-defined role, because the polymerization was slower with ZnCl₂. One difference is that upon ZnCl₂ addition, the MgCl₂ generated is insoluble and precipitates out of solution. In contrast, the generated Mg(OPiv)₂ remains in solution, and may form a mixed aggregate with the organozinc monomer.²⁵




FIGURE 2. Iodine quenching studies for polymerizations with and without $\text{Zn}(\text{OPiv})_2$. Plots depict changes in monomer conversion (%) versus time (s).

To support a chain-growth mechanism, the change in the M_n over time was monitored by SEC, which revealed monomodal and symmetric peaks shifting to a lower retention time during the polymerization (e.g., see Figure S10). More specifically, a linear increase in M_n versus conversion was observed, along with a constant \mathcal{D} , both of which are indicative of a chain-growth mechanism (Figure 3A). Changing the $[\text{monomer}]/[\text{precatalyst}]$ ratio enabled us to target specific molar masses ranging from 5 to 50 kg/mol (Figure 3B). Combined with the MALDI-TOF-MS study shown above, in which exclusively H/Br end groups are observed, these results are all consistent with a chain-growth polymerization mechanism.




FIGURE 3. Plots of M_n and \mathcal{D} versus (A) monomer conversion and (B) $[\text{monomer}]_0/[\text{catalyst}]$ ratio.

To determine whether our polymerization was living, a simple chain-extension experiment was performed. That is, a second batch of monomer was added after the first batch of monomer had polymerized. SEC analysis before and after the second addition of monomer displayed the expected increase in M_n while maintaining symmetrical SEC peaks, consistent with a living polymerization (Figure 4). To further challenge the system, a third batch of monomer was added, again showing the expected increase in M_n without any significant broadening of the dispersity. As a consequence, this living polymerization method may be useful to prepare sequenced copolymers, such as block and gradient copolymers.

Until this point, most of the experiments were performed on a small scale (<0.5 mmol monomer), which can be more challenging than larger scales due to quenching with adventitious moisture or contact with air. As a consequence, we scaled the reaction to approx. 5 mmol monomer, which should generate 0.5 g of P3HT. As anticipated, the reaction proceeded quite well, giving a M_n close to the targeted molar masses (9.4 versus 7.6 kg/mol, respectively) and a narrow dispersity ($\mathcal{D} = 1.34$). Isolating the polymer was more challenging, however, due to leftover monomer. However, after a series of precipitation steps, pure P3HT was isolated in 68% yield. Overall, this method is viable for generating significant quantities of P3HT for use in applications.




FIGURE 4. SEC traces for the chain extension experiment.

CONCLUSIONS

A living, chain-growth synthesis of poly(3-hexylthiophene) was developed using the air-stable Pd-PEPSSI-IPent precatalyst combined with moisture-tolerant organozinc monomer. Using this approach, polymers with predictable molar masses, moderate dispersities, and high

end-group fidelity were obtained. The living, chain-growth nature of this polymerization was corroborated by performing a chain-extension experiment, highlighting the potential of this approach for synthesizing block and gradient copolymers. We anticipate that this method may be useful for other monomer types. In addition, this method should be more accessible to a broader community of researchers due to the air/moisture tolerance and lack of need for specialized equipment. As researchers continue to explore CPs for varied applications, living, chain-growth methods like this one will be at the forefront.

ACKNOWLEDGEMENTS

We gratefully acknowledge the National Science Foundation (CHE-1565840) for funding this work. K. D. S. thanks the National Science Foundation for a predoctoral graduate research fellowship and M. D. H. thanks the Department of Defense for a National Defense Science and Engineering Graduate fellowship.

REFERENCES AND NOTES

- Shirakawa, E. J. Louis, A. G. MacDiarmid, C. K. Chiang, A. J. Heeger, Synthesis of Electrically Conducting Organic Polymers- Halogen Derivatives of Polyacetylene, (CH)_x. *J. Chem. Soc., Chem. Commun.* **1977**, 578–580.
- H. Sirringhaus, 25th Anniversary Article: Organic Field-Effect Transistors: The Path Beyond Amorphous Silicon. *Adv. Mater.* **2014**, *26*, 1319–1335.
- Y. Tsubata, Recent Progress of High Performance Polymer OLED and OPV Materials for Organic Printed Electronics. *Sci. Technol. Adv. Mater.* **2014**, *15*, 034203.
- G. Wang, F. S. Melkonyan, A. Facchetti, T. J. Marks, All-polymer Solar Cells: Recent Progress, Challenges, and Prospects. *Angew. Chem. Int. Ed.* **2019**, *58*, 4129–4142.
- T. M. Swager, 50th Anniversary Perspective: Conducting/Semiconducting Conjugated Polymers. A Personal Perspective on the Past and the Future. *Macromolecules* **2017**, *50*, 4867–4886.
- T. B. Schon, B. T. McAllister, P.-F. Li, D. S. Seferos, The Rise of Organic Electrode Materials for Energy Storage. *Chem. Soc. Rev.* **2016**, *45*, 6345–6404.
- F. Babudri, G. M. Farinola, F. Naso, Synthesis of Conjugated Oligomers and Polymers: The Organometallic Way. *J. Mater. Chem.* **2004**, *14*, 11–34.
- A. Yokoyama, R. Miyakoshi, T. Yokozawa, Chain-Growth Polymerization for Poly(3-hexylthiophene) with a Defined Molecular Weight and a Low Polydispersity. *Macromolecules* **2004**, *37*, 1169–1171.

- ⁹ E. E. Sheina, J. Liu, M. C. Iovu, D. W. Laird, R. D. McCullough, Chain Growth Mechanism for Regioregular Nickel-Initiated Cross-Coupling Polymerizations. *Macromolecules* **2004**, *37*, 3526–3528.
- ¹⁰ K. Okamoto, C. K. Luscombe, Controlled Polymerizations for the Synthesis of Semiconducting Conjugated Polymers. *Polym. Chem.* **2011**, *2*, 2424–2434.
- ¹¹ Z. J. Bryan, A. J. McNeil, Conjugated Polymer Synthesis via Catalyst-Transfer Polycondensation (CTP): Mechanism, Scope, and Applications. *Macromolecules* **2013**, *46*, 8395–8405.
- ¹² A. Kiriya, V. Senkovskyy, M. Sommer, Kumada Catalyst-Transfer Polycondensation: Mechanism, Opportunities, and Challenges. *Macromol. Rapid Commun.* **2011**, *32*, 1503–1517.
- ¹³ A. K. Leone, A. J. McNeil, Matchmaking in Catalyst-Transfer Polycondensation: Optimizing Catalysts based on Mechanistic Insight. *Acc. Chem. Res.* **2016**, *49*, 2822–2831.
- ¹⁴ M. A. Baker, C.-H. Tsai, K. J. T. Noonan, Diversifying Cross-Coupling Strategies, Catalysts and Monomers for the Controlled Synthesis of Conjugated Polymers. *Chem. Eur. J.* **2018**, *24*, 13078–13088.
- ¹⁵ J. P. Lutz, M. D. Hannigan, A. J. McNeil, Polymers Synthesized via Catalyst-Transfer Polymerization and their Applications. *Coord. Chem. Rev.* **2018**, *376*, 225–247.
- ¹⁶ A. K. Leone, E. A. Mueller, A. J. McNeil, The History of Palladium-Catalyzed Cross-Couplings Should Inspire the Future of Catalyst-Transfer Polymerization. *J. Am. Chem. Soc.* **2018**, *140*, 15126–15139.
- ¹⁷ S. Ye, S. Cheng, A. A. Pollit, M. W. Forbes, D. S. Seferos, Isolation of Living Conjugated Polymer Chains. *J. Am. Chem. Soc.* **2020**, *142*, 11244–11251.
- ¹⁸ A. Ichige, H. Saito, J. Kuwabara, T. Yasuda, J.-C. Choi, T. Kanbara, Facile Synthesis of Thienopyrroledione-Based π -Conjugated Polymers via Direct Arylation Polycondensation under Aerobic Conditions. *Macromolecules* **2018**, *51*, 6782–6788.
- ¹⁹ G. Magnin, J. Clifton, F. Schoenebeck, A General and Air-tolerant Strategy to Conjugated Polymers within Seconds under Palladium(I) Dimer Catalysis. *Angew. Chem. Int. Ed.* **2019**, *58*, 10179–10183.
- ²⁰ J. Kuwabara, T. Kanbara, Facile Synthesis of π -Conjugated Polymers via Direct Arylation Polycondensation. *Bull. Chem. Soc. Jpn.* **2019**, *92*, 152–161.
- ²¹ Higashihara, T.; Goto, E.; Ueda, M. Purification-free and protection-free synthesis of regioregular poly(3-hexylthiophene) and poly(3-(6-hydroxyhexyl)thiophene) using a zincate complex of $t\text{Bu}_4\text{ZnLi}_2$. *ACS Macro Lett.* **2012**, *1*, 167–170.
- ²² M. G. Organ, S. Avola, I. Dubovyk, N. Hadei, E. A. B. Kantchev, C. J. O’Brein, C. A. Valente, User-Friendly, All-Purpose Pd–NHC (NHC = N-Heterocyclic Carbene) Precatalyst for the Negishi Reaction: A Step Towards a Universal Cross-Coupling Catalyst. *Chem. Eur. J.* **2006**, *12*, 4749–4755.
- ²³ C. Valente, M. E. Belowich, N. Hadei, M. G. Organ, Pd-PEPSI Complexes and the Negishi Reaction. *Eur. J. Org. Chem.* **2010**, 4343–4354.
- ²⁴ C. Valente, S. Çalimsiz, K. H. Hoi, D. Mallik, M. Sayah, M. G. Organ, The Development of Bulky Palladium NHC Complexes for the Most-Challenging Cross-Coupling Reactions. *Angew. Chem. Int. Ed.* **2012**, *51*, 3314–3332.
- ²⁵ A. Hernán-Gómez, E. Herd, E. Hevia, A. R. Kennedy, P. Knochel, K. Koszinowski, S. M. Manolikakes, R. E. Mulvey, C. Schnegelsberg, Organozinc Pivalate Reagents: Segregation, Solubility, Stabilization, and Structural Insights. *Angew. Chem. Int. Ed.* **2014**, *53*, 2706–2710.
- ²⁶ Y.-H. Chen, M. Ellwart, V. Malakhov, P. Knochel, Solid Organozinc Pivalates: A New Class of Zinc Organometallics with Greatly Enhanced Air- and Moisture-Stability. *Synthesis* **2017**, *49*, 3215–3223.

²⁷ M. Ellwart, Y.-H. Chen, C. P. Tüllmann, V. Malakhov, P. Knochel, Preparation of Solid Organozinc Pivalates and their Reaction in Pd-Catalyzed Cross-Couplings. *Org. Syn.* **2018**, *95*, 127–141.

²⁸ S. Bernhardt, G. Manolikakes, T. Kunz, P. Knochel, Preparation of Solid Salt-Stabilized Functionalized Organozinc Compounds and their Application to Cross-Coupling and Carbonyl Addition Reactions. *Angew. Chem. Int. Ed.* **2011**, *50*, 9205–9209.

²⁹ C. I. Stathakis, S. Bernhardt, V. Quint, P. Knochel, Improved Air-Stable Solid Aromatic and Heterocyclic Zinc Reagents by Highly Selective Metalations for Negishi Cross-Couplings. *Angew. Chem. Int. Ed.* **2012**, *51*, 9428–9432.

³⁰ S. M. Manolikakes, M. Ellwart, C. I. Stathakis, P. Knochel, Air-Stable Solid Aryl and Heteroaryl Organozinc Pivalates: Syntheses and Applications in Organic Synthesis. *Chem. Eur. J.* **2014**, *20*, 12289–12297.

³¹ Note that SEC measurements relative to PS standards are known to over-estimate the M_n of P3HT by a factor of ~ 1.3 , see ref: M. Wong, J.

Hollinger, L. M. Kozycz, T. M. McCormick, Y. Lu, D. C. Burns, D. S. Seferos, An Apparent Size-Exclusion Quantification Limit Reveals a Molecular Weight Limit in the Synthesis of Externally Initiated Polythiophenes. *ACS Macro. Lett.* **2012**, *1*, 1266–1269.

³² K. Gu, J. Onorato, S. S. Xiao, C. K. Luscombe, Y.-L. Loo, Determination of the Molecular Weight of Conjugated Polymers with Diffusion-Ordered NMR Spectroscopy. *Chem. Mater.* **2018**, *30*, 570–576.

³³ A. K. Leone, P. K. Goldberg, A. J. McNeil, Ring-Walking in Catalyst-Transfer Polymerization. *J. Am. Chem. Soc.* **2018**, *140*, 7846–7850.

³⁴ M.G. Organ, Çalimsiz, S.; Sayah, M; Hoi, K. H.; Lough, A. J. Pd-PEPPSI-IPent: An Active, Sterically Demanding Cross-Coupling Catalyst and Its Application in the Synthesis of Tetra-ortho-Substituted Biaryls. *Angew. Chem. Int. Ed.* **2009**, *48*, 2383–2387.


³⁵ Hardeman, T.; Koeckelberghs, G. Synthesis of Conjugated Copolymers by Combining Different Coupling Reactions. *Polym. Chem.* **2017**, *8*, 3999–4004.

GRAPHICAL ABSTRACT

Tomohiro Kubo, Kendra D. Souther, Morgan S. Young, Matthew D. Hannigan, and Anne J. McNeil

Air-Tolerant Poly(3-hexylthiophene) Synthesis via Catalyst-Transfer Polymerization

Transition metal-mediated cross-coupling polymerizations typically require inert atmospheres to attenuate premature monomer quenching and/or catalyst deactivation. Herein, poly(3-hexylthiophene) is synthesized without the need for an inert atmosphere by using bench-stable Pd precatalysts and organozinc pivalates. The reaction yields polymers with specified molar masses and end-group identities, as well as with narrow dispersities, consistent with a living, chain-growth polymerization.



GRAPHICAL ABSTRACT

Tomohiro Kubo, Kendra D. Souther, Morgan S. Young, Matthew D. Hannigan, and Anne J. McNeil

Air-Tolerant Poly(3-hexylthiophene) Synthesis via Catalyst-Transfer Polymerization

Transition metal-mediated cross-coupling polymerizations typically require inert atmospheres to attenuate premature monomer quenching and/or catalyst deactivation. Herein, poly(3-hexylthiophene) is synthesized without the need for an inert atmosphere by using bench-stable Pd precatalysts and organozinc pivalates. The reaction yields polymers with specified molar masses and end-group identities, as well as with narrow dispersities, consistent with a living, chain-growth polymerization.

